Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2016-11-28-01** **Date: 29/11/2016**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Construction of Samudaya Bhavana at Hegdenagara (near Dry Waste collection center) in ward no.06, Byatarayanapura sub division.

Agency : Sri.P.Hemanth (Soorya Creaters), #109/110, 4th Cross, 6th main, Vivekananda Road, Balaji layout, Nagashettyhalli, Sanjaynagara, Bangalore-94

Customer's Reference : BBMP/EE/BTP/WO/48/2016-17

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 28-11-16

Sample ID No : 2016-11-28-01/01

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/11/2016

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M20	22/11/2016	29/11/2016	149.85 X 150.44 X 150.23	22543	8.158	390.0	17.3	17.3
2	Roof Concrete	M20	22/11/2016	29/11/2016	150.47 X 150.44 X 149.82	22637	8.135	396.1	17.5	
3	Roof Concrete	M20	22/11/2016	29/11/2016	150.37 X 150.28 X 150.49	22598	8.152	386.4	17.1	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

Page 1/1
****End of Report****